

Novel method to prepare multiwalled carbon nanotube/poly(dimethyl siloxane) (MWCNT/PDMS) non-conducting composites

Goswami, Kaustav; Daugaard, Anders Egede; Skov, Anne Ladegaard

Publication date:
2014

[Link back to DTU Orbit](#)

Citation (APA):

Goswami, K., Daugaard, A. E., & Skov, A. L. (2014). Novel method to prepare multiwalled carbon nanotube/poly(dimethyl siloxane) (MWCNT/PDMS) non-conducting composites. Abstract from 4th International Conference on Electromechanically Active Polymer (EAP) Transducers & Artificial Muscles, Linköping, Sweden.

DTU Library Technical Information Center of Denmark

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Novel method to prepare multiwalled carbon nanotube/poly(dimethyl siloxane) (MWCNT/PDMS) non-conducting composites

K Goswami, A E Daugaard, A L Skov

DTU, The Danish Polymer Centre, Department of Chemical and Biochemical Engineering, Kgs. Lyngby, Denmark

In this study a new method of carbon nanotube (CNT) incorporation was employed for the preparation of ultraviolet (UV) curable CNT filled poly (dimethyl siloxane) (PDMS) composites. The composites were designed to contain loadings of CNT above the percolation threshold without becoming conductive due to a localized distribution of CNT. Ultrasonicated and dispersed multiwalled CNTs were mixed with short chain α,ω - vinyl terminated PDMS. When the whole mixture containing dispersed CNT and short chain PDMS was irradiated with UV radiation in presence of deficient amount of hexa functional thiol PDMS crosslinker and a photoinitiator, hyperbranched PDMS layer was formed over the CNTs. The prepared hyperbranched CNTs were mixed in different weight ratios (0.33%, 0.66%, 1%) with long chain α,ω - vinyl terminated PDMS and crosslinked subsequently with the same hexa functional thiol PDMS via UV photoinitiated thiol-ene chemistry to obtain the networks. Rheology of the prepared networks showed a gradual decrease in storage modulus (G') in the entire frequency range as the amount of CNT was increased due to a reduction in crosslinking density imposed by the CNTs. Dielectric spectroscopy measurements showed an increasing trend in permittivity in all the composites with increasing CNT loadings and AC conductivity measurements confirmed non-percolating behavior of the prepared composites.